



## Product Specification **7195**

Taconic 7195 is a 1mm open mesh PTFE coated fabric recommended for applications which require superior release and controlled porosity for rapid drying. This fabric is specifically designed for use in high temperature forced hot air curing ovens for processing textiles and other materials. Maximum width is 72"

Product Properties	Units	Value	Tolerance	Test Method
Reinforcing Substrate		<b>E-GLASS</b>		
Coating Type		<b>PTFE</b>		
% Coating	%	<b>21</b>	+/- 2%	
Total Coated Weight	lbs/yd <sup>2</sup>	<b>0.95</b>	+/- 5%	ASTM D4969
Nominal Thickness	inch	<b>0.019</b>		ASTM D4969
Tensile Strength	lbf/in	<b>200</b>	Typical Warp	ASTM D902
		<b>185</b>	Minimum Warp	
		<b>190</b>	Typical Fill	
		<b>175</b>	Minimum Fill	
Win Open Size (length)	inch	<b>0.0394</b>		
Win Open Size (Width)	inch	<b>0.0394</b>		
Opening Area	%	<b>25</b>		
Operating Temperature	°Fahrenheit	<b>-100° to +500°</b>		

Information contained in this document is based on our general experience and is given in good faith, but we are unable to accept responsibility in respect to factors which are outside our knowledge or control. All data is subject to change without notice.

**This product is suitable for direct and repeated use in a food contact application when used in accordance with the product specifications.**



ISO 9001  
#3083

Please contact us for samples or a quotation

### Taconic Headquarters

Petersburg, NY  
[www.4taconic.com](http://www.4taconic.com)  
[info@4taconic.com](mailto:info@4taconic.com)



### Western US, Mexico & Central America

La Verne, CA  
[www.4taconic.com](http://www.4taconic.com)  
[info@4taconic.com](mailto:info@4taconic.com)

For queries in Europe please visit [www.taconic-ipd.com](http://www.taconic-ipd.com)  
 or email [info@taconic-ipd.com](mailto:info@taconic-ipd.com)

### Canada

Mississauga, CAN  
[www.4taconic.com](http://www.4taconic.com)  
[info@4taconic.com](mailto:info@4taconic.com)

