



Product Specification **A952**

Taconic A952 is a 3 mil PTFE coated fiberglass fabric complete with a premium coated weight of PTFE. This material exhibits release properties, heat resistance, chemical resistance, and allows for good heat transfer. Common applications include heat sealing/poly packaging, tray lining, composite release liners, gaskets and seals, and a variety of aerospace applications. Currently produced at 38" wide.

Product Properties	Units	Value	Tolerance	Test Method
Reinforcing Substrate		E-GLASS		
Coating Type		PTFE		
% Coating		70	+/- 2%	
Total Coated Weight	lbs/yd ²	0.3	+/- 5%	ASTM D4969
Nominal Thickness	inch	0.0031		ASTM D4969
Dielectric Breakdown	Volts/Mil	1135	Typical	ASTM D149 Method A
		700	Minimum	
Tensile Strength	lbf/in	92	Typical Warp	ASTM D902
		75	Minimum Warp	
		62	Typical Fill	
		40	Minimum Fill	
Tear Strength	lbs	2.1	Typical Warp	ASTM D5587
		1.2	Minimum Warp	
		0.97	Typical Fill	
		0.5	Minimum Fill	
Operating Temperature	°Fahrenheit	-100° to +500°		

Information contained in this document is based on our general experience and is given in good faith, but we are unable to accept responsibility in respect to factors which are outside our knowledge or control. All data is subject to change without notice.

This product is suitable for direct and repeated use in a food contact application when used in accordance with the product specifications.



ISO 9001
#3083

Taconic Headquarters

Petersburg, NY
www.4taconic.com
info@4taconic.com



Please contact us for samples or a quotation

Western US, Mexico & Central America

La Verne, CA
www.4taconic.com
info@4taconic.com

For queries in Europe please visit www.taconic-ipd.com
 or email info@taconic-ipd.com

Canada

Mississauga, CAN
www.4taconic.com
info@4taconic.com

